



Product Data Sheet

Handwrap Stretch Film / CAST

Technical Data

Gauge		60	67	70	80	90	115	
Elmendorf Tear (Gms./Sht)	MD	45.8	56.2	60.6	75.4	90.2	127.2	ASTM D1922
	TD	508.1	508.4	508.5	508.8	509.1	509.9	
Haze (%)		1.62	1.66	1.68	1.73	1.79	1.92	ASTM D1003
Gloss 45 (%)		90.6	90.7	90.8	90.9	91.1	91.5	ASTMD 2457
Ultimate Tensile (PSI)	MD	8220.1	8034.3	7954.6	7689.1	7423.6	6759.8	ASTM D882
	TD	3797.5	3801.5	3803.4	3809.2	3815.1	3829.8	
Maximum Elongation (%)	MD	478.1	494.3	501.2	524.4	547.5	605.3	ASTM D882
	TD	870.5	879.9	883.7	896.8	910.0	942.9	
Dart Drop (Gms./Sht)		65.7	69.6	71.3	77.0	82.7	96.8	ASTM D1709